



Achieve the innovative value of paint

JIAZHI® Easy-cleaning functional resin

Model number

JIAZHI®JZ-9910

Specification

Composition	Silicon modified polyurethane acrylic resin
Appearance	Transparent to slight yellowish liquid
Solvent	BAC
Content	50±3%(140°C 2h)
Density	1.00-1.04g/ml(25±1)°C
Viscosity	5-50s (T-4 viscometer)(25±0.2)°C

Note: This data sheet is intended to give typical results, not standard. Subject to COA.

Application system

UV cure

Properties

- Increase slip. Improve hydrophobicity and oleophobicity.
- Provide anti-marker wiping performance.
- High hardness and transparency.
- Improve scratch resistance.
- Provide lotus leaf effect. Water contact angle > 100°
- Excellent leveling.
- Excellent adhesive.
- Excellent solvent resistance. After 100 times of alcohol wiping, the surface of the paint film can still keep the effect of dry rubbing without residue.

Recommended formula

material	Dosage %
JIAZHI®JZ-9910	96.00
UV photoinitiator	4.00
Total	100.00

Storage stability

Should be placed in a cool and dry place, unopened in the original packaging for 24 months. Products beyond the storage period may continue to be used after inspection. The container must be closed immediately after use.

Package

25KG / 180KG